

3M™ Thermally Conductive Adhesive Tape 8904

Product Description

3M™ Thermally Conductive Adhesive Tape (TCAT) 8904 are 0.20mm, 0.25mm, and 0.50mm thickness pressure sensitive adhesive tapes filled with thermally conductive ceramic particles and flame retardant fillers. This product is specially designed to have good converting ability, handling and re-workability through the introduction of thin PET carrier. The 8904 TCAT is designed with a soft acrylic polymer and multiple thickness options to allow excellent wet-out or conformability to many surface conditions. The 8904 TCAT has good adhesion performance to many substrate types and has excellent dielectric performance. The 3M 8904 is a hybrid TCAT that offer greater thickness ranges than the 3M 8820 TCAT thermal tape (maximum 0.5mm thickness), and has thickness options similar to the 3M™ Acrylic Thermal Pads, such as the 5570 Acrylic Thermal Pad, but with higher adhesion performance that allow additional design and assembly flexibility.

Product Uses

This product can be used for heat management of electronic devices for general heat dissipation device and other bonding/joining parts in electronic products.

Key Features

- Good thermal conductivity (>1.5W/m-K)
- Excellent dielectric performance
- Low thermal impedance
- Good and reliable adhesion performance against Al and SUS
- Vibration damping

Product Construction

Product	3M™ Thermally Conductive Adhesive Tape 8904
Adhesive Type	Soft Acrylic Adhesive
Tape Thickness	0.20mm / 0.25mm / 0.50mm
Tape Color	White (slightly grey dotted)
Filler Type	Ceramic Particle
Product Liner	75 µm PET Liner
Roll Length	Standard: 40MT (0.20mm, 0.25mm & 0.50mm) Custom size can be supplied by request.



Application Ideas

- General Heat Sink Bonding
- IC Chip Packaging Heat Conduction
- Printed Circuit Board
- LED module/ board bonding
- Flat Panel Display TV as LCD and PDP
- COF Chip Heat Conduction
- Mechanical fastening such as clamp, bracket, screw can be used in parallel with this thermal conductive tape.

Typical Physical Properties and Performance Characteristics

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Product		3M™ Thermally Conductive Tape 8904		
ASTM D-3330 90 Angle Peel Adhesion Crosshead speed : 508mm/min 72 hr dwell at 70°C SUS 304 test substrate		Unit : gram/25.4mm width		
	Liner side	0.20	0.25	0.50
	Non-liner side	>2000	>2000	>2000
ASTM D-1002 Dynamic Shear Crosshead speed : 305mm/min	Initial Adhesion (SUS to SUS)	Unit : Kg/6.25cm²		
		>15		
Foam Density (gram/cm³)		1.60 (±0.10)		
Dielectric Strength (KV/mm)		15		
Flammability (UL94)		V0 (QMFZ2.E239181)		
Thermal Conductivity (W/m-K on plane direction)		>1.50		
Operating Temperature Range* 3M Test Method	Long Term (Weeks-Months)	Up to 80°C		
	Short Term (Hours-Days)	Up to 90°C		

***Note:** The end use customer application, design & verification testing will determine the final in use effective temperature range based on each application's environmental conditions.

Application Techniques

- Bond strength is dependent upon the amount of adhesive to surface contact developed. Firm application pressure helps to develop better adhesive contact and improve bonding strength.
- To obtain optimum adhesion, the bonding surfaces must be clean, dry and well unified. Typical surface cleaning solvents are isopropyl alcohol and water (rubbing alcohol) or heptane. **Note:** Be sure to follow manufacturer's safety precautions and directions for use when using solvents.
- Ideal tape application temperature range is 21°C to 38°C (70°F to 100°F). Initial tape application to surfaces at temperatures below 10°C (50°F) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

Regulatory

For regulatory information about this product, refer to our website at 3M.com.

For Additional Information

To request additional product information or to arrange for sales assistance, call toll free 1-800-251-8634. Address correspondence to: 3M, Electronics Markets Materials Division, 3M Center, Building 225-3S-06, St. Paul, MN 55144-1000. Our fax number is 651-778-4244 or 1-877-369-2923. In Canada, phone: 1-800-364-3577. In Puerto Rico, phone: 1-787-750-3000. In Mexico, phone: 52-70-04-00.

Technical Information

The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use

Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer

Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability

Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.



Electronics Markets Materials Division

3M Center, Building 225-3S-06
St. Paul, MN 55144-1000
1-800-251-8634 phone
651-778-4244 fax
www.3M.com/electronics

3M is a trademark of 3M Company.
Please recycle. Printed in U.S.A.
© 3M 2013. All rights reserved.
60-5002-0560-8

